

No.: GZIN1807040503MR

Date: Aug 03, 2018

Page: 1 of 4

CUSTOMER NAME: GUANGDONG GUANG SO TECHNOLOGY CO., LTD

ADDRESS: HUAXING SCIENCE PARK, WAIJINGINDUSTRIAL PARK, NIU SHAN

COMMUNITY, DONGCHENG STREET, DONGGUAN CITY,

GUANGDONG PROVINCE

Sample Name : PVC COMPOUND

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : CP18-041014

Date of Receipt : Jul 26, 2018

Testing Start Date : Jul 26, 2018

Testing End Date : Aug 03, 2018

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. GZ Branch Testing Center

Ruby Luo

Authorized signatory





No.: GZIN1807040503MR

Date: Aug 03, 2018

Page: 2 of 4

Summary of Results:


No.	Test Item	Test Method	Result	Conclusion
1	Light Ageing Test-UV Exposure	ISO 4892-3:2016 Cycle1 & ISO 105- A02:1993/Cor.2:2005	Grey scale: 3-4	/

Note: Pass : Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:







No.: GZIN1807040503MR

Date: Aug 03, 2018

Page: 3 of 4

Test Item: Light Ageing Test-UV Exposure

Sample Description: See photo

Test Method: ISO 4892-3:2016 Cycle1 & ISO 105-A02:1993/Cor.2:2005

Test Condition:

Exposure cycle:

ISO 4892-3:2016 cycle 1 Lamp type: UVA-340

8h UV at (60±3)°C BPT, 0.76W/(m²•nm)@340nm

4h condensation at (50±3)°C BPT


Exposure duration: 96h

Test Result:

Sample	Grey scale
A	3-4

Note: According to ISO 105-A02:1993/Cor.2:2005, the grey scale was determined under the D65 standard light, with scale 5 as the best and scale 1 as the worst.

Test Photo:





18Kahu Road, Glaimach Park Gangzhou Economic & Technology Development District, Guengzhou, Chine 510663 t (88-20) 82155555 t (86-20) 82075188 www.sgsgroup.com.cn 中国・广州・经济技术开发区科学城科珠路198号 邮第:510663 t (86-20) 82155555 t (86-20) 82075188 e sgs.china@sgs.com



No.: GZIN1807040503MR

Date: Aug 03, 2018

Page: 4 of 4

Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration
_qa.pon				date
UV Accelerated	QUV-Se	GZMR-AG-E188	2018-04-17	2019-04-16
Weathering Tester				
Colour Assessment	CAC60	GZMR-AG-E003	2018-06-21	2019-06-20
Cabinet				

Appendix information:

The results of this test report were copied from the report No. GZIN1807039683MR.

****** End of report******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service prints overleaf, available on request or accessible at http://www.sac.com/en/Terms-and-Conditions.grap, and conditions for Electronic Documents at http://www.sac.com/en/Terms-and-Conditions/Terms-e-Document.asy.
Attention is drawn to the limitation of liability, indemnification and jurisdiction issues define therein. Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. An unauthorized attention, forger or faisification of the content results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention. To check the authenticity of testing dispacetion report & certificate please contents us at templone (84-75518307144).